

MARAZZI  **USA**

the fine art of porcelain stoneware

(lounge14™)

color body porcelain stoneware
rectified |  printing technique

Made In The USA



Spritzer



Cosmopolitan



Sidecar



Martini



Spritzer Decorative Inlay



Cosmopolitan Decorative Inlay



Sidecar Decorative Inlay



Martini Decorative Inlay



Spritzer Mosaic - Strip



Cosmopolitan Mosaic - Strip



Sidecar Mosaic - Strip



Martini Mosaic - Strip



Spritzer Mosaic - Square 2"x2"



Cosmopolitan Mosaic - Square 2"x2"



Sidecar Mosaic - Square 2"x2"



Martini Mosaic - Square 2"x2"



	FLOOR TILE			DECOS		TRIMS				
Thickness	12"x24" R (30x60 cm) 3/8" (10mm)	9"x36" R (22.5x90 cm) 3/8" (10mm)	18"x36" R (45x90 cm) 3/8" (10mm)	12"x24" R (30x60 cm) Decorative Inlay	12"x24" (30x60 cm) Mosaic - Strip	12"x12" (30x30 cm) Mosaic - Square 2"x2"	3"x24" (8x60 cm) Bullnose	6"x12" (15x30 cm) Cove Base	1"x6" (2.5x30 cm) Cove Base Out Angle	
Names (colors)										
Cosmopolitan (Beige)	ULGN	ULGS	ULGW	ULJA	ULJJ	ULJE	ULH2	ULH6	ULHE	
Martini (Black)	ULGP	ULGT	ULGX	ULJB	ULJK	ULJF	ULH3	ULH7	ULHF	
Sidecar (Grey)	ULGQ	ULGU	ULGY	ULJC	ULJL	ULJG	ULH4	ULH8	ULHG	
Spritzer (White)	ULGR	ULGV	ULGZ	ULJD	ULJM	ULJH	ULH5	ULH9	ULHH	

ASTM Test Results

Technical Characteristics	ASTM Standards	ASTM Test Results	ASTM Test Methods
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	7.5	MOHS Scale
Breaking Strength	≥ 250 lbf.	≥ 696 lbf.	C648
Facial Dimension	-3.0% < Nominal ≤ 2.0%	Within Standard	C499
Nominal Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (squareness)	+/- 0.25% or +/- 0.8 mm**	Within Standard	C502
Warpage (flatness)	+/- 0.40% or +/- 1.8 mm**	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
DCOF-Dynamic Coefficient of Friction (Wet Areas Only)*	As Reported	Minimum 0.42	DCOF AcuTest SM *
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

*Dynamic Coefficient of Friction (DCOF) - Water, oil, grease or other fluids create slippery conditions. When installing floors in areas with exposure to these conditions, a minimum D.C.O.F. value of 0.42 is required. Additionally, extra caution is required with regards to product selection and proper maintenance. Visit www.tcnatile.com for complete information regarding the DCOF AcuTest test method and values.

**DCOF AcuTest is the industry designation for the test procedure contained in ANSI A137.1 Section 9.6, which has been extensively researched, allows for in-situ field measurements, and is in use at tile manufacturing facilities. It was so named to distinguish it from other DCOF measurements using different instruments and/or protocols.

** Whichever is less

